



Tipo BAC



CK45 / 1.1191

Referencia Type	Diámetro Diameter	Peso Weight	Longitud Estándar Length	Tolerancia Estándar Tolerance	Rectitud Straightness	Espesor cromo Chrome Thickness
	Ø d mm	Kg/M	mm	ISO f7 µm	t1 µm	µm
BAC8*	8	0,40	6 000	-13/-28	0,3	
BAC10	10	0,62	6 000	-16/-34	0,3	20+/-5
BAC12	12	0,89	6 000		0,2	20+/-5
BAC16	16	1,58	6 000		0,2	20+/-5
BAC18	18	2,00	6 000	-20/-41	0,2	20+/-5
BAC20	20	2.47	6 000		0,2	20+/-5
BAC22	22	2.98	6 000		0,2	20+/-5
BAC25	25	3.86	6 000		0,2	20+/-5
BAC30	30	5.55	6 000	-25/-50	0,2	20+/-5
BAC35	35	7.56	6 000		0,2	20+/-5
BAC40	40	9.87	6 000		0,2	20+/-5
BAC45	45	12.52	6 000		0,2	20+/-5
BAC50	50	15.42	6 000	-30/-60	0,2	20+/-5
BAC60*	60	22.19	6 000		0,2	20+/-5
BAC70*	70	30.21	6 000			20+/-5
BAC80*	80	39.49	6 000		0,2	20+/-5

Dureza del cromo Chrome layer Hardness 900 - 1100 HV

Ø Disponible en stock Ø available on stock

\* Consultar \*On request

